



### CERTIFICATION OF TRANSLATION

I, Kyung-ae Lee, an employee of Y.P. LEE, MOCK & PARTNERS of Cheonghwa Bldg., 1571-18 Seocho-dong, Seocho-gu, Seoul, Republic of Korea, hereby declare under penalty of perjury that I understand the Korean language and the English language; that I am fully capable of translating from Korean to English and vice versa; and that, to the best of my knowledge and belief, the statement in the English language in the attached translation of Korean Patent Application No. 10-2002-0051157 consisting of 19 pages, have the same meanings as the statements in the Korean language in the original document, a copy of which I have examined.

Signed this 8th day of February 2006

Kyung-ae Lee



## ABSTRACT

### [Abstract of the Disclosure]

A water-soluble, antimicrobial active polymer and an ink composition comprising  
5 the same are provided. The polymer is prepared by coupling an antimicrobial active  
compound to a branch of polyvinylalcohol and provides excellent antimicrobial effect  
without affecting the properties of the ink composition comprising the polymer. The  
polymer is added to the ink composition in an amount of 1 to 10 parts by weight based  
on 100 parts by weight of the ink composition. The ink composition provides extended  
10 storage stability due to no coagulation, good antimicrobial effect even in a printed  
picture, and no irritation to human skin.

### [Index Words]

Polyvinylalcohol, 3-aminopropyltriethoxysilane,  
15 3-(2-aminoethyl)aminopropyltrimethoxysilane

## SPECIFICATION

[Title of the Invention]

5           Watersoluble polymer antibiotic agent and ink composition comprising the same

[Detailed Description of the Invention]

[Object of the Invention]

[Technical Field of the Invention and Related Art prior to the Invention]

10           The present invention relates to a water-soluble, antimicrobial active polymer, and more particularly, to a water-soluble polymer with antimicrobial activity, resulting from introducing an antimicrobial active compound into a water-soluble polymer. The present invention also relates to an ink composition comprising the water-soluble, antimicrobial active polymer.

15           Generally, antimicrobial agents are applied to products that have frequent contact with water such as fibers, shoes, sponge gourds, and medical goods. Such antimicrobial agents are designed to have washing resistance or water-insoluble characteristic in order to maintain antimicrobial effects. For this reason, such antimicrobial agents had not been applied to water-soluble ink compositions.

20           Ink compositions comprise a colorant, a solvent and an additive. When stored for a long duration, ink properties and storage stability of ink compositions deteriorate due to reproduction and growth of bacteria in the ink. For this reason, an antimicrobial agent is separately added to ink compositions. Conventionally, organic compounds such as 1,2-benzisothiazolin-3-one (BIT) and methyl 2-benzimidazole carbamate  
25 (Carbendazim) are widely used as antimicrobial and preserving agents. They are separately added to ink compositions in an amount of 0.05-0.5% by weight for the purpose of extended storage duration. However, a nozzle is easily clogged due to ink coagulation and the homogeneity of ink droplets cannot be easily secured. Furthermore, when human skin is in contact with such ink compositions, skin irritation  
30 may occur. Therefore, handling property is deteriorated. Meanwhile, in case of using

another antimicrobial agents with lower antimicrobial activity to overcome these problems, extended storage stability is decreased. Furthermore, it is difficult to select dyes or pigments which are well compatible with such antimicrobial agents. As a result, an optimal color quality cannot be easily accomplished.

5

#### [Technical Goal of the Invention]

The present invention provides a water-soluble polymer with excellent antimicrobial activity and storage stability. When added to an ink composition, the water-soluble polymer does not adversely affect physical properties of the ink composition.

10


The present invention also provides an ink composition comprising the water-soluble polymer.

#### [Structure and Operation of the Invention]

15

In accordance with an aspect of the present invention, there is provided a water-soluble, antimicrobial active polymer represented by the formula 1:

Formula 1




wherein:

20

n and m are the number of repeated units, n is 0.7-0.95 and m is 0.05-0.3 provided that n+m=1; and

R<sub>1</sub> is a silane derivative represented by the formula 2:

Formula 2



wherein:

R<sub>2</sub> is alkyl of 1-30 carbon atoms, heteroalkyl of 1-30 carbon atoms, aryl of 6-20 carbon atoms, arylalkyl of 6-20 carbon atoms, heteroaryl of 6-30 carbon atoms, or  
 5 heteroarylalkyl of 6-30 carbon atoms, each of which is unsubstituted or substituted with halogen, hydroxyl, nitro, cyano, amino, amidino, hydrazine, hydrazone, carboxylic acid or a salt thereof, sulfonic acid or a salt thereof, phosphoric acid or a salt thereof, alkyl of 1-20 carbon atoms, alkenyl, alkynyl, heteroalkyl of 1-20 carbon atoms, aryl of 6-20 carbon atoms, arylalkyl of 6-30 carbon atoms, heteroaryl of 6-30 carbon atoms, or  
 10 heteroarylalkyl of 6-30 carbon atoms;


R<sub>3</sub> is alkyl of 1-12 carbon atoms, alkenyl or alkynyl of 1-12 carbon atom, or heteroalkyl of 1-12 carbon atoms, each of which is unsubstituted or substituted with halogen, hydroxyl, nitro, cyano, amino, amidino, hydrazine, hydrazone, carboxylic acid or a salt thereof, sulfonic acid or a salt thereof, phosphoric acid or a salt thereof, alkyl of  
 15 1-20 carbon atoms, alkenyl, alkynyl, heteroalkyl of 2-20 carbon atoms, aryl of 6-20 carbon atoms, arylalkyl of 6-30 carbon atoms, heteroaryl of 6-30 carbon atoms, or heteroarylalkyl of 6-30 carbon atoms;

R<sub>4</sub> and R<sub>5</sub> are independently hydrogen, or alkyl of 1-5 carbon atoms; and

R<sub>6</sub> is hydrogen, hydroxyl, or alkoxy of 1-5 carbon atoms.


20 According to specific embodiments of the present invention, the silane derivative of the formula 2 is a compound represented by the formula 3:

Formula 3




4: The silane derivative of the formula 2 is a compound represented by the formula

Formula 4:




5: The silane derivative of the formula 2 is a compound represented by the formula

Formula 5



10 6: The silane derivative of the formula 2 is a compound represented by the formula

Formula 6



15 According to another aspect of the present invention, there is provided an ink composition comprising the water-soluble, antimicrobial active polymer of the present invention in an amount of 1 to 10 parts by weight.

Hereinafter, the present invention will be described in more detail.

The water-soluble, antimicrobial active polymer of the present invention is obtained by introducing a silane derivative with excellent antimicrobial activity into a branch of a polyvinylalcohol which is used as a wetting agent or a thickening agent in a

water-soluble ink. Unlike a conventional antimicrobial agent which is separately added to an ink composition, the water-soluble, antimicrobial active polymer is added to an ink composition as a moiety of the polyvinylalcohol. Therefore, the water-soluble, antimicrobial active polymer provides a water-soluble ink with excellent antimicrobial activity without affecting the properties of a water-soluble ink.

The silane derivative of the formula 2 has at least two hydroxyl or alkoxy groups. It can be obtained via the formation of an amide bond between a dicarboxylic acid and 3-aminopropyltriethoxysilane, 3-aminopropyltrihydroxysilane, 3-(2-aminoethyl)aminopropyltrihydroxysilane, or 3-(2-aminoethyl)aminopropyltriethoxysilane. The dicarboxylic acid as used herein has a substituted or unsubstituted alkyl of 1-30 carbon atoms, a substituted or unsubstituted heteroalkyl of 1-30 carbon atoms, a substituted or unsubstituted aryl of 6-20 carbon atoms, a substituted or unsubstituted arylalkyl of 6 to 30 carbon atoms, a substituted or unsubstituted heteroaryl of 6-30 carbon atoms or a substituted or unsubstituted heteroarylalkyl of 6-30 carbon atoms.

The water-soluble, antimicrobial active polymer of the present invention is obtained by reacting polyvinylalcohol with the antimicrobial active silane derivative of the formula 2. As a result, the antimicrobial active silane derivative is introduced into a branch of the polyvinylalcohol. The silane derivative as used herein is generally used as an antimicrobial agent, a wetting agent and a surfactant. It is mainly used as a surface cleaning solution. In particular, it is known to have an excellent antimicrobial activity.

The term, "alkyl" as used herein refers to a straight or branched chain group of 1-30 carbon atoms, preferably a straight or branched chain group of 1-20 carbon atoms, and more preferably a straight or branched chain group of 1-12 carbon atoms. Examples of the alkyl include methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, t-butyl, pentyl, isoamyl, hexyl, heptyl, octyl, nonyl, decyl and dodecyl. One or more hydrogen atoms on the alkyl may be substituted by halogen, hydroxyl, nitro, cyano, amino, amidino, hydrazine, hydrazone, carboxylic acid or a salt thereof, sulfonic

acid or a salt thereof, phosphoric acid or a salt thereof, alkyl of 1-20 carbon atoms, alkenyl, alkynyl, heteroalkyl of 1-20 carbon atoms, aryl of 6-20 carbon atoms, arylalkyl of 6-30 carbon atoms, heteroaryl of 6-30 carbon atoms, or heteroarylalkyl of 6-30 carbon atoms.

5           The term, "alkenyl" or "alkynyl" as used herein refers to a straight or branched chain group containing a carbon-carbon double bond or triple bond in a central portion or one end of the alkyl as defined in the above. Examples of such groups include ethylene, propylene, butylene, hexylene and acetylene.

10           The term, "heteroalkyl" as used herein refers to a straight or branched chain group containing nitrogen, sulfur, oxygen or phosphorus in the alkyl as defined in the above. Examples of the heteroalkyl include methoxy, ethoxy, propoxy, butoxy and t-butoxy. Examples of the heteroalkyl having a substituted group include a haloalkoxy compound such as fluoromethoxy, chloromethoxy, trifluoromethoxy, trifluoroethoxy, fluoroethoxy and fluoropropoxy. One or more hydrogen atoms on the heteroalkyl may  
15 be substituted by halogen, hydroxyl, nitro, cyano, amino, amidino, hydrazine, hydrazone, carboxylic acid or a salt thereof, sulfonic acid or a salt thereof, phosphoric acid or a salt thereof, alkyl of 1-20 carbon atoms, alkenyl, alkynyl, heteroalkyl of 2-20 carbon atoms, aryl of 6-20 carbon atoms, arylalkyl of 6-30 carbon atoms, heteroaryl of 6-30 carbon atoms, or heteroarylalkyl of 6-30 carbon atoms.

20           The term, "aryl" as used herein, which is used alone or in combination, refers to an aromatic compound of 6-20 carbon atoms containing one or more rings. The rings may be attached to each other as a pendant group or may be fused. The aryl is an aromatic compound such as phenyl, naphthyl, tetrahydronaphthyl, indane, and biphenyl. Preferable aryl is phenyl or naphthyl. The aryl may have a substituent such as  
25 hydroxyl, halo, haloalkyl, nitro, cyano, alkoxy and lower alkylamino. One or more hydrogen atoms on the aryl may be substituted by halogen, hydroxyl, nitro, cyano, amino, amidino, hydrazine, hydrazone, carboxylic acid or a salt thereof, sulfonic acid or a salt thereof, phosphoric acid or a salt thereof, alkyl of 1-20 carbon atoms, alkenyl,



alkynyl, heteroalkyl of 1-20 carbon atoms, aryl of 6-20 carbon atoms, arylalkyl of 6-30 carbon atoms, heteroaryl of 6-30 carbon atoms, or heteroarylalkyl of 6-30 carbon atoms.

The term, "arylalkyl" as used herein refers to a lower alkyl, for example methyl, ethyl and propyl appended to the aryl as defined in the above. Examples of the arylalkyl include benzyl and phenylethyl. One or more hydrogen atoms on the arylalkyl may be substituted by halogen, hydroxyl, nitro, cyano, amino, amidino, hydrazine, hydrazone, carboxylic acid or a salt thereof, sulfonic acid or a salt thereof, phosphoric acid or a salt thereof, alkyl of 1-20 carbon atoms, alkenyl, alkynyl, heteroalkyl of 1-20 carbon atoms, aryl of 6-20 carbon atoms, arylalkyl of 6-30 carbon atoms, heteroaryl of 6-30 carbon atoms, or heteroarylalkyl of 6-30 carbon atoms.

The term, "heteroaryl" as used herein refers to a monovalent monocyclic or bicyclic aromatic compound of 6-30 carbon atoms containing one, two or three hetero atoms selected from N, O, P or S. Examples of the heteroaryl include, but are not limited to, thienyl, benzothienyl, pyridyl, pyrazinyl, pyrimidinyl, pyridazinyl, quinolynyl, quinoxalynyl, imidazolyl, furanyl, benzofuranyl, thiazolyl, isoxazolyl, benzisoxazolyl, benzimidazolyl, triazolyl, pyrazolyl, pyrrolyl, indolyl, 2-pyridonyl, 4-pyridonyl, N-alkyl-2-pyridonyl, pyrazynonyl, pyridazynonyl, pyrimidinonyl, oxazolonyl, and N-oxide thereof (for example, pyridyl N-oxide, quinolynyl N-oxide) and quaternary salt thereof. One or more hydrogen atoms on the heteroaryl may be substituted by halogen, hydroxyl, nitro, cyano, amino, amidino, hydrazine, hydrazone, carboxylic acid or a salt thereof, sulfonic acid or a salt thereof, phosphoric acid or a salt thereof, alkyl of 1-20 carbon atoms, alkenyl, alkynyl, heteroalkyl of 1-20 carbon atoms, aryl of 6-20 carbon atoms, arylalkyl of 6-30 carbon atoms, heteroaryl of 6-30 carbon atoms, or heteroarylalkyl of 6-30 carbon atoms.

The term, "heteroarylalkyl" as used herein refers to a lower alkyl group appended to the heteroaryl as defined in the above. One or more hydrogen atoms on the heteroarylalkyl may be substituted by halogen, hydroxyl, nitro, cyano, amino, amidino, hydrazine, hydrazone, carboxylic acid or a salt thereof, sulfonic acid or a salt thereof, phosphoric acid or a salt thereof, alkyl of 1-20 carbon atoms, alkenyl, alkynyl,

heteroalkyl of 1-20 carbon atoms, aryl of 6-20 carbon atoms, arylalkyl of 6-30 carbon atoms, heteroaryl of 6-30 carbon atoms, or heteroarylalkyl of 6-30 carbon atoms.

The ink composition of the present invention comprises the water-soluble, antimicrobial active polymer of 1 to 10 parts by weight based on 100 parts by weight of the ink composition. If the content of the polymer is 1 part by weight or less, desired antimicrobial effect cannot be accomplished. On the other hand, if it exceeds 10 parts by weight, properties of the ink composition are adversely affected.

The ink composition of the present invention comprises a colorant, an aqueous medium, and a dispersing agent. Generally, polyvinylalcohol is used as a dispersing agent. The water-soluble polymer of the present invention acts as an antimicrobial agent in addition to as a dispersing agent. The ink composition may further comprise one or more dispersing agents (referred to as "secondary dispersing agent", hereinafter) except for the polyvinylalcohol to secure dispersibility or storage stability of the colorant. Although there are no particular limitations on the secondary dispersing agent, it is preferable to use dispersing agents with simple structure and low molecular weight in terms of physical properties and storage stability of the ink composition. Examples of the secondary dispersing agent include, but are not limited to, polyvinylalcohol (PVA), cellulosics, ethylene oxide modified phenol, ethylene oxide/propylene oxide polymer, a sodium polyacrylate solution (TEGO, disperse 715W), a modified polyacryl resin solution (TEGO, disperse 735W), solution of an alkylol ammonium salt of a low molecular weight polycarboxylic acid polymer (BYK-Chemie, Disperbyk), solution of an alkylol ammonium salt of polyfunctional polymer (BYK-Chemie, Disperbyk-181) or a mixture thereof. A high molecular weight dispersing agent such as a block copolymer may also be used.

In the ink composition of the present invention, an aqueous medium is used as a solvent. The aqueous medium is water alone or water in combination with one or more organic solvents. The organic solvent is present in an amount of 5 to 50 parts by weight based on 100 parts by weight of the ink composition. The content of water and organic solvent depends on various factors, for example viscosity, surface tension, and

drying speed of the ink composition. The content may also vary depending on a printing method and type of a substrate on which the ink is printed.

Examples of the organic solvent mainly used in the aqueous medium include alcohol such as methyl alcohol, ethyl alcohol, n-propyl alcohol, isopropyl alcohol, n-butyl alcohol, sec-butyl alcohol, t-butyl alcohol, and isobutyl alcohol; ketones such as acetone, methylethyl ketone, and diacetone alcohol; ester such as ethyl acetate and ethyl lactate; polyhydric alcohol such as ethyleneglycol, diethyleneglycol, triethyleneglycol, propyleneglycol, butyleneglycol, 1,4-butanediol, 1,2,4-butanetriol, 1,5-pentanediol, 1,2,6-hexanetriol, hexyleneglycol, glycerol, glycerol ethoxylate, and trimethylolpropane ethoxylate; lower alkyl ether such as ethyleneglycol monomethyl ether, ethyleneglycol monoethyl ether, diethyleneglycol methyl ether, diethyleneglycol ethyl ether, triethyleneglycol monomethyl ether, and triethyleneglycol monoethyl ether; nitrogen-containing compound such as 2-pyrrolidone and N-methyl-2-pyrrolidone; and sulfur-containing compound such as dimethyl sulfoxide, tetramethylenesulfone and thioglycol.

The ink composition of the present invention may further comprise an additive such as a viscosity modifier, a surfactant, a storage stabilizer, a wetting agent and a metal oxide.

The viscosity modifier acts to modify viscosity in order to maintain a smooth jetting of the ink. Examples of the viscosity modifier include casein and carboxymethylcellulose. The viscosity modifier is added to the ink composition in an amount of 0.1 to 5.0 parts by weight based on 100 parts by weight of the ink composition.

The surfactant acts to stabilize the jetting performance of the ink from a nozzle by adjusting the surface tension of the ink composition. An anionic or a non-ionic surfactant may be used.

Examples of the anionic surfactant include an alkylcarboxylic acid salt of 1-1,000 carbon atoms and preferably 10-200 carbon atoms, an alcohol sulfonic acid ester salt of 1-1,000 carbon atoms and preferably 10-200 carbon atoms, an alkylsulfonic acid salt of

1-1,000 carbon atoms and preferably 10-200 carbon atoms, an alkylbenzenesulfonic acid salt of 1-1,000 carbon atoms and preferably 10-200 carbon atoms and a mixture thereof. Examples of the non-ionic surfactant include polyoxyethylene alkyl ether wherein the alkyl moiety has 1-1,000 carbon atoms and preferably 10-200 carbon atoms, polyoxyethylene alkyl phenyl ether wherein the alkyl moiety has 1-1,000 carbon atoms and preferably 10-200 carbon atoms, polyoxyethylene secondary alcohol ether, polyoxyethylene-oxypropylene blockcopolymer, polyglycerine fatty acid ester, sorbitan fatty acid ester, and a mixture thereof. The surfactant is added to the ink composition in an amount of 0.1 to 5 parts by weight based on 100 parts by weight of the ink composition.

The wetting agent is used to prevent clogging of a nozzle. Examples of the wetting agent include polyhydric alcohol such as glycerine, ethylene glycol, diethylene glycol, triethylene glycol, propylene glycol, dipropylene glycol, hexylene glycol, 1,3-butanediol, 1,4-butanediol, 1,5-pentanediol, 2-buten-1,4-diol, 2-methyl-2-pentanediol and a mixture thereof. The wetting agent is added to the ink composition in an amount of 5 to 40 parts by weight based on 100 parts by weight of the ink composition.

The ink composition of the present invention can be prepared using the components as mentioned the above as the following procedure.

First, a water-soluble, antimicrobial active polymer, a colorant, a dispersing agent, a viscosity modifier and a surfactant are mixed while stirring in an aqueous medium to obtain a homogeneous mixture. Then, the mixture is filtered through a filter of a pore size of 0.45 to 1.0  $\mu\text{m}$  to prepare the ink composition of the present invention.

Hereinafter, the present invention will be described with reference to the following examples and experiments but is not limited thereto.

#### Example 1

300 ml of dimethylsulfoxide (DMSO, Junsei Co.) as a solvent was poured into a rounded bottom flask. 22 g of 3-aminopropyl triethoxysilane (Aldrich Co.) and 16 g of adipic acid (Aldrich) were added to the flask and mixed. The flask was then heated at

120°C under a nitrogen atmosphere for 8 hours. Then, 43 g of polyvinylalcohol of degree of polymerization of 300-500 (PVA, average Mw: 13,000-23,000, Aldrich) was added and heated at 80°C. Then, the DMSO was added until the PVA was completely dissolved. When the PVA was completely dissolved, the mixture was heated at 110°C under a nitrogen atmosphere for 6 hours. The resultant mixture was cooled to room temperature, precipitated in excess methanol, and filtered. The filtrate was dried to yield a 35 g of a water-soluble, antimicrobial active polymer.

#### Example 2

A water-soluble, antimicrobial active polymer was prepared in the same manner as in Example 1 except for using 16 g of phthalic anhydride (Aldrich) instead of adipic acid. The water-soluble, antimicrobial active polymer yielded 33 g.

#### Example 3

A water-soluble, antimicrobial active polymer was prepared in the same manner as in Example 1 except for using 22 g of [3-(2-aminoethyl)aminopropyl]trimethoxysilane (Aldrich) instead of 3-aminopropyltriethoxysilane. The water-soluble, antimicrobial active polymer yielded 31 g.

#### Example 4

A water-soluble, antimicrobial active polymer was prepared in the same manner as in Example 3 except for using 16 g of phthalic anhydride instead of adipic acid. The water-soluble, antimicrobial active polymer yielded 32 g.

#### Example 5

##### Component

C. I. Direct Black 168

Water

##### Content

4.0 g

78 g

Isopropylalcohol	3 g
Water-soluble, antimicrobial active polymer of Example 1	4.0 g

All the components were mixed and thoroughly stirred in a mechanical agitator for 30 minutes or more to obtain a homogeneous mixture. The resultant mixture was  
5 filtered through a filter with a pore size of 0.45  $\mu\text{m}$  to obtain a desired ink composition.

#### Example 6

An ink composition was prepared in the same manner as in Example 5 except for using C. I. Pigment Red 177 instead of C. I. Direct Black 168 and a filter with a pore size  
10 of 1.0  $\mu\text{m}$  instead of 0.45  $\mu\text{m}$ .

#### Example 7

An ink composition was prepared in the same manner as in Example 5 except for using C. I. Direct Black 51 instead of C. I. Direct Black 168.

#### Comparative example 1

An ink composition was prepared in the same manner as in Example 5 except for using polyvinylalcohol of degree of polymerization of 300-500 (PVA, Aldrich) instead of the water-soluble, antimicrobial active polymer of Example 1.

#### Comparative example 2

An ink composition was prepared in the same manner as in Example 6 except for using polyvinylalcohol of degree of polymerization of 300-500 (PVA, Aldrich) instead of the water-soluble, antimicrobial active polymer of Example 1.

### Comparative example 3

An ink composition was prepared in the same manner as in Example 7 except for using polyvinylalcohol of degree of polymerization of 300-500 (PVA, Aldrich) instead of the water-soluble, antimicrobial active polymer of Example 1.

5

Properties of ink compositions of Examples 5-7 and Comparative examples 1-3 were measured according to the following method.

### Experiment 1

100 ml of each ink composition of Examples 5-7 and Comparative examples 1-3 was placed in a thermostable glass bottle, sealed, and deposited in a 60°C thermostatic bath. After two months, the presence of a precipitate was observed and the results are presented in Table 1 below.

15

Table 1

	Example 5	Example 6	Example 7	Comparative 1	Comparative 2	Comparative 3
Storage stability	O	O	O	Δ	X	Δ

Comparative : Comparative example

O : no precipitates, Δ : fine precipitates, X: coarse precipitates

### Experiment 2

TA98 was added to each ink composition of Examples 5-7 and Comparative examples 1-3 and kept in a dark room at 37°C for 48 hours. The number of colonies was calculated and the results are presented in Table 2 below.

20

Table 2

Example 5	Example 6	Example 7	Comparative 1	Comparative 2	Comparative 3
-----------	-----------	-----------	---------------	---------------	---------------

Number of colonies	78	83	81	356	372	395
Comparative : Comparative example						


### [Effect of the Invention]

As apparent from the above description, unlike a conventional antimicrobial agent with strong toxicity and poor ink miscibility being separately added to ink compositions, the antimicrobial active polymer of the present invention is prepared by coupling an antimicrobial active compound to a branch of a conventional polymer used as a wetting agent or the like. As a result, the antimicrobial active polymer of the present invention provides excellent antimicrobial effect without affecting the properties of ink compositions comprising the polymer, in particular, extended storage stability. In particular, because the antimicrobial active polymer has a lowered toxicity due to the coupling, droplets of ink compositions do not irritate the human skin. In addition, a printed picture also exhibits an antimicrobial effect for an extended duration.



What is claimed is:


1. A water-soluble, antimicrobial active polymer represented by the formula 1:



5 wherein:

n and m are the number of repeated units, n is 0.7-0.95 and m is 0.05-0.3 provided that n+m=1; and

R<sub>1</sub> is a silane derivative represented by the formula 2:



10 wherein:

R<sub>2</sub> is alkyl of 1-30 carbon atoms, heteroalkyl of 1-30 carbon atoms, aryl of 6-20 carbon atoms, arylalkyl of 6-20 carbon atoms, heteroaryl of 6-30 carbon atoms, or heteroarylalkyl of 6-30 carbon atoms, each of which is unsubstituted or substituted with halogen, hydroxyl, nitro, cyano, amino, amidino, hydrazine, hydrazone, carboxylic acid or a salt thereof, sulfonic acid or a salt thereof, phosphoric acid or a salt thereof, alkyl of 1-20 carbon atoms, alkenyl, alkynyl, heteroalkyl of 2-20 carbon atoms, aryl of 6-20 carbon atoms, arylalkyl of 6-30 carbon atoms, heteroaryl of 6-30 carbon atoms, or heteroarylalkyl of 6-30 carbon atoms;


R<sub>3</sub> is alkyl of 1-12 carbon atoms, alkenyl or alkynyl of 1-12 carbon atom, or heteroalkyl of 1-12 carbon atoms, each of which is unsubstituted or substituted with halogen, hydroxyl, nitro, cyano, amino, amidino, hydrazine, hydrazone, carboxylic acid or a salt thereof, sulfonic acid or a salt thereof, phosphoric acid or a salt thereof, alkyl of

1-20 carbon atoms, alkenyl, alkynyl, heteroalkyl of 1-20 carbon atoms, aryl of 6-20 carbon atoms, arylalkyl of 6-30 carbon atoms, heteroaryl of 6-30 carbon atoms, or heteroarylalkyl of 6-30 carbon atoms;


R<sub>4</sub> and R<sub>5</sub> are independently hydrogen, or alkyl of 1-5 carbon atoms; and

R<sub>6</sub> is hydrogen, hydroxyl, or alkoxyl of 1-5 carbon atoms.


2. The water-soluble, antimicrobial active polymer according to claim 1, wherein the silane derivative of the formula 2 is a compound represented by the formula 3:




3. The water-soluble, antimicrobial active polymer according to claim 1, wherein the silane derivative of the formula 2 is a compound represented by the formula 4:



4. The water-soluble, antimicrobial active polymer according to claim 1, wherein the silane derivative of the formula 2 is a compound represented by the formula 5:



5. The water-soluble, antimicrobial active polymer according to claim 1, wherein the silane derivative of the formula 2 is a compound represented by the formula 6:



6. An ink composition comprising:  
a water-soluble, antimicrobial active polymer according to any one of claims 1-5;  
a colorant; and  
an aqueous medium.

7. The ink composition according to claim 6, wherein the water-soluble, antimicrobial active polymer is added to the ink composition in an amount of 1 to 10 parts by weight based on 100 parts by weight of the ink composition.

8. The ink composition according to claim 6, wherein the aqueous medium is water alone or water in combination with one or more organic solvents.

9. The ink composition according to claim 8, wherein the organic solvent is selected from the group consisting of alcohol such as methyl alcohol, ethyl alcohol, n-propyl alcohol, isopropyl alcohol, n-butyl alcohol, sec-butyl alcohol, t-butyl alcohol, and isobutyl alcohol; ketones such as acetone, methylethyl ketone, and diacetone alcohol; ester such as ethyl acetate and ethyl lactate; polyhydric alcohol such as ethyleneglycol, diethyleneglycol, triethyleneglycol, propyleneglycol, butyleneglycol, 1,4-butanediol, 1,2,4-butanetriol, 1,5-pentanediol, 1,2,6-hexanetriol, hexyleneglycol, glycerol, glycerol ethoxylate, and trimethylolpropane ethoxylate; lower alkyl ether such

as ethyleneglycol monomethyl ether, ethyleneglycol monoethyl ether, diethyleneglycol methyl ether, diethyleneglycol ethyl ether, triethyleneglycol monomethyl ether, and triethyleneglycol monoethyl ether; nitrogen-containing compound such as 2-pyrrolidone and N-methyl-2-pyrrolidone; and sulfur-containing compound such as dimethyl sulfoxide,  
5 tetramethylenesulfone and thioglycol.

10. The ink composition according to claim 6, further comprising a viscosity modifier, a surfactant, a storage stabilizer and a wetting agent.